



VALPAINT S.p.A.
Via dell'Industria, 80 - 60020 POLVERIGI (AN) ITALY
Tel. +39 071 906383 (r.a.) - Fax +39 071 906384
E-mail: info@valpaint.it
C.F./P.IVA/R.l. di AN 01108220425
Capitale Sociale € 500.000,00 i.v.

www.valpaint.it • www.valpaintjungle.it

SC 00236

VELIDOR FINE

Technical Sheet

NAME:

VELIDOR FINE

TYPE:

siloxane finish

USE

Water-based interior and exterior decoration

CHARACTERISTICS:

specific weight: 1.120 ± 30 gr/LT. at 20°C. (it may vary according to the roughness, surface absorption and application methods)

viscosity: = = =

yield : 25 - 30 m²/LT.

aesthetic effect: mat

colours: as per catalogue

packaging: LT. 1- LT.2,5- LT.5

DRYING:

on the surface: 1 hour at 20°C

over painting: 6 - 8 hours at 20°C

in depth: 24 - 36 hours at 20°C

CHARACTERISTICS AND RESISTANCE:

Siloxane veiled effect for decorating interior and exterior surfaces. VELIDOR FINE can be used to create exclusive, antique-style environments displaying the classic Renaissance style yet in line with recent decorative trends. VELIDOR FINE is breathable and washable, it can be painted over and is easy to apply with various tools (brush, glove, sponge, roller, etc.).

PREPARATION OF THE SURFACE:

Old Surfaces. Remove old non-adhering and peeling paint and wash using water and suitable soap products. Next, apply a coat of PRIMER 1200 diluted 50% with water to act as a fixative. After approximately 4 hours at 20°C, apply a second coat of PRIMER 1200 diluted 15 - 20% with water. If, however, the surfaces are clean and not peeling, apply one or two coats of PRIMER 1200 diluted 15 - 20% with water. After 4 hours at 20°C, proceed with the application of VELIDOR FINE.

PREPARATION OF THE PRODUCT:

New Surfaces. Use a filler to repair the surface. When dry, sand the surface then apply one or two coats of PRIMER 1200 diluted 15 - 20% with water. After 4 hours at 20°C, proceed with the application of VELIDOR FINE.

APPLICATION:

dilution: to be diluted 20 - 30% with water

system by brush - glove - sponge - roller

number of coatings: 1 or 2

Apply a coat of VELIDOR FINE in circular strokes using a brush or glove. Alternatively, VELIDOR FINE can be applied with criss-cross brush strokes in all directions. VELIDOR FINE can also be applied using a brush or roller and worked over with a sponge or glove soon afterwards, while the paint is still wet. If desired, a second coat of VELIDOR FINE can be applied after 6 - 8 hours at 20°C. VELIDOR FINE can be applied either over PRIMER 1200 (for interiors and exteriors) or directly on any other resin-rich paint that adheres properly to the surface, is in good condition and is not powdery.

Lastly, VELIDOR FINE can be used on BUCCIATO PLASTICO 539, PLASTICO LISCIO 509, ISOLPAINT M399 and ANTICANDO 300 or 600.

page 1 of 2



VALPAINT S.p.A.
Via dell'Industria, 80 - 60020 POLVERIGI (AN) ITALY
Tel. +39 071 906383 (r.a.) - Fax +39 071 906384
E-mail: info@valpaint.it
C.F./P.IVA/R.I. di AN 01108220425
Capitale Sociale € 500.000,00 i.v.

www.valpaint.it • www.valpaintjungle.it

SC00236

Application temperature: above +5°C and below +30°C. Do not apply under direct sunlight or in windy conditions. Avoid application during very humid days or on frozen surfaces. **Drying:** in a non-dusty environment for 1 hour at 20°C. Dry after 6 - 8 hours at 20°C. Hardens after 24 hours, depending on the temperature of the room.

Storage: make sure the tin is tightly closed, even after use, and stored at a temperature no lower than +10°C and no higher than +30°C.

Stability: approximately 2 years, if well sealed and never opened.

NOTE:

Stocking temperature and application temperature must be not inferior to +5°C and not superior to +30°C. Avoid application under beating sun or in case of strong wind. Avoid days with high humidity or frozen surfaces. Working tools must be washed immediately after use with water and soap.

Technical Sheet n° SC 00236 issued by the Control Quality Department

Edition n° 1

July 2012

page 2 of 2