



VALPAINT S.p.A.
Via dell'Industria, 80 - 60020 POLVERIGI (AN) ITALY
Tel. +39 071 906383 (r.a.) - Fax +39 071 906384
E-mail: info@valpaint.it
C.F./P.IVA/R.I. di AN 01108220425
Capitale Sociale € 500.000,00 i.v.

www.valpaint.it

SC 00029

PRIMART 300

Technical Sheet

NAME:

TYPE:

USE:

TECHNICAL DATA:

DRYING TIME:

CHARACTERISTICS AND RESISTANCE:

PREPARATION OF THE SURFACE:

PREPARATION OF THE PRODUCT:

APPLICATION:

PRIMART 300

mural primer, with a basis of odourless solvent for various kinds of surfaces, for example: wood, cement, plastic, glass, light alloys, iron. High level of washability. It is a special Primer created to get ancient effects of Arteco'9

specific weight: 1.400 ± 30 gr/lit at 25° C
viscosity: 20" Coppa Ford 8 at 25° C
yield: 7- 8 m²/lit
aspect: opaque
colours: white
packaging: cans of lt.1 - lt.5 - lt.12
on the surface: 1 hour at 20° C
over painting: 4 - 6 hours at 20° C
below the surface: 24 hours depending on atmospheric conditions

excellent resistance to atmospheric agents, also in extreme conditions (maritime climate, industrial zones). Insensitive to the alkaline (cause of the disintegration of the protection of paints), anti-mould, anti-bacterial. Resistant to water but gas-permeable (transpirability). High level of washability.

value the surface condition, taking off old and not anchored paints and plastering again where necessary. Fill in cracks and holes with Stucco Fast 150 (outdoor surfaces) or Valstuc (indoor surfaces). Apply a coat of antirust Wiktor on iron surfaces

thinning: ready for use; for spray application dilute approximately at 10% with odourless diluents ISOSAN 3A or odourless White Spirit.

catalization relation: = = =

pot life: = = =

system: with brush, roller or spray gun

coats: 1 - 2

NOTE:

Compared with traditional water paints, Primart 300 has the following advantages:

- 1) Does not contain water-sensitive (better resistance to water)
- 2) Does not contain biodegradable components (better resistance to water)
- 3) Is not affected by chemical products of smog (absorbs less dirt)
- 4) Can be applied in low temperatures to 0° C.
- 5) Is breathable and does not cause bubbles
- 6) Is therefore insensitive to the alkaline (frequent cause of the disintegration of the paint)
- 7) Penetrates deeper and so ensures better binding
- 8) Is not affected by rain

Technical Sheet n° SC 00029 issued by the Control Quality Dpt.:

Edition n° 5

July 2008