



VALPAINT S.p.A.
Via dell'Industria, 80 - 60020 POLVERIGI (AN) ITALY
Tel. +39 071 906383 (r.a.) - Fax +39 071 906384
C.F./P.IVA/ R.I. di AN 01108220425
Capitale Sociale € 500.000,00 i.v.
www.valpaint.it E-mail: info@valpaint.it

SC 00228

SABULADOR SOFT

Technical Sheet

<u>NAME:</u>	SABULADOR SOFT
<u>TYPE:</u>	luminescent effect paints
<u>USE:</u>	water based paint for interior decoration.
<u>CHARACTERISTICS:</u>	specific weight: 1.100 ± 30 gr/LT a 25°C viscosity: = = = yield: 9 - 12 m ² /LT (it may vary according to the roughness, porosity and surface absorption and the method of application) aesthetic effect: opalescent semi-gloss effect colours: ARGENTO 100, ORO 200, ALLUMINIO 300 and colours on catalogue packaging: LT. 1 - LT. 2,5 - LT. 5 on the surface: 1 hour at 20°C over-painting: 3 - 4 hours at 20°C below the surface: 24 hours at 20°C
<u>DRYING:</u>	
<u>CHARACTERISTICS AND RESISTENCE:</u>	It is a water-based paint for interiors, featuring exclusive luminous sandy reflections. SABULADOR SOFT can be used to create exclusive and elegant environments in line with new decorative trends, regardless of whether the overall style is modern or classic. SABULADOR SOFT is a very high-quality paint as it is breathable, washable and may be painted over with any other water-based paint. Old Surfaces. Remove old non-adhering and peeling paint and wash using water and a suitable soap product. Next, apply a coat of PRIMART 600 diluted 50% with water as a fixative. After approximately 4 hours at 20°C, apply a second coat of PRIMART 600 diluted 20 - 30% with water. If, however, the surfaces are clean and not peeling, apply a single coat of PRIMART 600 diluted 15 - 20% with water. After 4 hours at 20°C, proceed with the application of SABULADOR SOFT. New Surfaces. Use a filler to repair the surface. When dry, sand the surface then apply a coat of PRIMART 600 diluted 15 - 20% with water. After 4 hours at 20°C, proceed with the application of SABULADOR SOFT.
<u>PREPARATION OF THE SURFACE:</u>	thinning: ready to use
<u>PREPARATION OF THE PRODUCT:</u>	catalization relations: = = = pot life: = = = system: brush number coating: 1 - 2
<u>APPLICATION:</u>	
<u>APPLICATION CYCLE:</u>	To create the colours displayed in the catalogue, mix the SABULADOR SOFT Col. SILVER 100 or Col. GOLD 200 with the corresponding amount of COLORI' colouring paste. Alternatively, the VALCLONE paint-mixing system may be used to achieve the desired colour. Brushstroke Effect: apply SABULADOR SOFT using the PV 09 Brush and work in all directions. Allow to dry for about 2 hours at 20°C, then apply a second coat using the same technique.

page 1 of 2



VALPAINT S.p.A.
Via dell'Industria, 80 - 60020 POLVERIGI (AN) ITALY
Tel. +39 071 906383 (r.a.) - Fax +39 071 906384
C.F./P.IVA/ R.I. di AN 01108220425
Capitale Sociale € 500.000,00 i.v.
www.valpaint.it E-mail: info@valpaint.it

SC 00228

APPLICATION CYCLE:

Streaked Effect: apply SABULADOR SOFT using the PV 95 Roller and work in all directions; on the last stroke, move in a vertical direction from top to bottom. Go over the product while it is still wet using the PV 88 or PV 89 Spatula, moving from top to bottom and vice-versa to leave streaks which are as straight as possible. Allow to dry for about 2 hours at 20°C, then apply a second coat using the same Roller and Spatula techniques.

Storage: make sure the tin is tightly closed, even after use, and stored at a temperature no lower than +10°C and no higher than +30°C.

Stability: approximately 2 years in a tight closed tin not opened

NOTES:

The temperature of the application must be between +5°C and +30°C. Tools must be cleaned soon after use with water and soap.

Technical sheet n° SC 00228 issued by the Control Quality Manager:

Edition n° 1

January 2011

page 2 of 2