



VALPAINT S.p.A.  
Via dell'Industria, 80 - 60020 POLVERIGI (AN) ITALY  
Tel. +39 071 906383 (r.a.) - Fax +39 071 906384  
C.F./P.IVA/ R.I. di AN 01108220425  
Capitale Sociale € 500.000,00 i.v.  
[www.valpaint.it](http://www.valpaint.it) E-mail: [info@valpaint.it](mailto:info@valpaint.it)

SC 00152

## PRIMART 600

### Technical sheet

**NAME:**

**PRIMART 600**

**TYPE:**

transpiring water-based primer for interiors and exteriors

**USE:**

professional white water-base paint characterised by a high-covering and whiteness It is a special primer created to get ancient effects typical of ARTECO' 7.

**TECHNICAL DATA:**

**specific weight:** 1.515 ± 30 gr/LT. at 25°C

**viscosity:** = = =

**yield :** 10 - 12 m<sup>2</sup>/LT.

**aesthetic effect:** matt

**colours:** white (it is possible to colour the paint using COLORI' or colours for water-base systems resistant to UV rays)

**packaging:** LT. 1 - LT. 2,5 - LT. 5

**DRYING TIME:**

**on the surface:** 30 minutes at 20°C

**overpainting:** 2 hours at 20°C

**below the surface:** 12 hours at 20°C

**CHARACTERISTICS AND**

It well resists to rural and marine atmosphere.

**RESISTENCE:**

It does not prevent wall transpiration.

**PREPARATION OF THE**

Remove old badly-adhering or peeling paint and wash using a suitable soap product. Use a suitable filler to repair the surface where necessary. When the filler is dry, after approximately 4 hours at 20°C, apply a coat of PRIMART 600 diluted 50% with water as a fixative. After approximately 4 hours at 20°C, apply a second coat of PRIMART 600 diluted 15 - 20% with water. If, however, the surfaces are not chalking or peeling, apply a coat of PRIMART 600 diluted 15 - 20% with water once the filler has dried.

**SUPPORT:**

On new walls use a suitable filler to repair the surface where necessary. When the filler is dry, after approximately 4 hours at 20°C, sand the surface then apply a coat of PRIMART 600 diluted 15 - 20% with water.

**PREPARATION OF THE**

**dilution:** 15 - 20% with drinkable water on the basis of the weight

**PRODUCT:**

**catalization relation:** = = =

**pot life:** = = =

**APPLICATION:**

**system:** brush - roller - spray gun

**coats:** 1 - 2

**stability:** Approximately 2 years , if well sealed and never opened.

**NOTES:**

Application temperature must be between +5°C and +30°C. Wash tools soon after used with soap and water. Keep away from freezing.

Technical Sheet n° SC 00152 issued by the Control Quality Department

Edition n° 5

April 2010