



VALPAINT S.p.A.
Via dell'Industria, 80 - 60020 POLVERIGI (AN) ITALY
Tel. +39 071 906383 (r.a.) - Fax +39 071 906384
E-mail: info@valpaint.it
C.F./P.IVA/R.I. di AN 01108220425
Capitale Sociale € 500.000,00 i.v.

www.valpaint.it • www.valpaintjungle.it

SC 00152

PRIMART 600

Technical sheet

NAME:

PRIMART 600

TYPE:

transpiring water-based primer for interiors.

USE:

professional white water-base paint characterised by a high covering and whiteness It is a special primer created to get ancient effects typical of ARTECO'7.

TECHNICAL DATA:

specific weight: 1.515 ± 30 gr/LT. at 25°C

viscosity: = = =

yield : 10 - 12 m²/LT.

aesthetic effect: matt

colours: white (it is possible to colour the paint using COLORI' or colours for water-base systems resistant to UV rays)

DRYING TIME:

packaging: LT. 1 - LT. 2,5 - LT. 5

on the surface: 30 minutes at 20°C

overpainting: 2 hours at 20°C

below the surface: 12 hours at 20°C

CHARACTERISTICS AND RESISTENCE:

It well resists to rural and marine atmosphere. It does not prevent wall transpiration.

PREPARATION OF THE SUPPORT:

Remove old badly-adhering or peeling paint and wash using a suitable soap product. Use a suitable filler to repair the surface where necessary. When the filler is dry, after approximately 4 hours at 20°C, apply a coat of PRIMART 600 diluted 50% with water as a fixative. After approximately 4 hours at 20°C, apply a second coat of PRIMART 600 diluted 15 - 20% with water. If, however, the surfaces are not chalking or peeling, apply a coat of PRIMART 600 diluted 15 - 20% with water once the filler has dried.

On new walls use a suitable filler to repair the surface where necessary. When the filler is dry, after approximately 4 hours at 20°C, sand the surface then apply a coat of PRIMART 600 diluted 15 - 20% with water.

PREPARATION OF THE PRODUCT:

dilution: 15 - 20% with drinkable water on the basis of the weight

catalization relation: = = =

pot life: = = =

APPLICATION:

system: brush - roller - spray gun

coats: 1 - 2

stability: Approximately 2 years, if well sealed and never opened.

NOTES:

Application temperature must be between +5°C and +30°C. Wash tools soon after used with soap and water. Keep away from freezing.

Technical Sheet n° SC 00152 issued by the Control Quality Department

Edition n° 6

July 2012